

C. L. Hauthaway & Sons Corporation
638 Summer Street Lynn, MA 01905-2092

781 592-6444
www.hauthaway.com

Hauthane HD-2120

- DESCRIPTION:** A very hard, aliphatic, polyester polyurethane dispersion.
- SUGGESTED USES:** **HD-2120** was developed for use on flexible and rigid PVC. Coatings containing this polymer form hard, tough, hydrolysis-, chemical- and stain-resistant films, which approach 2-component polyurethane performance levels. Superior adhesion to PVC makes it the ideal candidate for automotive interior parts, vinyl furniture and components.
- CHARACTERISTICS:** Superior adhesion to PVC
Excellent UV resistance
Exceptional alcohol resistance
Humidity resistance
Contains n-methyl pyrrolidone co-solvent
- APPLICATION:** **HD-2120** can be used as a sole vehicle or blended with acrylic emulsions for spray, dip or rotogravure applications. It can be thickened with associative thickeners for alternative application methods.
- DRYING:** The addition of coalescing solvent is recommended to achieve optimal film formation with **HD-2120**. In ambient-cured systems the addition of 5-10% coalescing solvent is suggested. Less coalescing solvent is required in heat-cured systems to attain comparable film properties. Typical drying temperatures and dwell times for aqueous coatings are sufficient to optimize film characteristics.

PHYSICAL PROPERTIES

SOLIDS	35%(±1%)
VISCOSITY	50-500 cps
DENSITY	8.8 lbs/gal
pH	7.5 - 10.0
SOFTENING POINT	355° F
VOC CONTENT	337 g/l (less water)
SWARD HARDNESS	52

TENSILE PROPERTIES

(TESTED AT 2 INCHES/MINUTE)	
ELONGATION	35 %
TENSILE STRENGTH	8500 psi
100% MODULUS	NA
200% MODULUS	NA
300% MODULUS	NA