

C. L. Hauthaway & Sons Corporation  
638 Summer Street Lynn, MA 01905-2092

781 592-6444  
www.hauthaway.com

## Hauthane HD-6000

**DESCRIPTION:** A polyester-based, hydroxyl-functional, aliphatic, water-borne polyurethane dispersion.

**SUGGESTED USES:** **HD-6000** was developed for use with water-dispersible, isocyanate crosslinkers such as Bayer's Bayhydur 302 or Perstrop's Easaqua X D 401 / M 501. The product, when crosslinked provides tough, chemical resistant, glossy coatings which may be applied to a variety of substrates including concrete, metals, plastics and wood materials. This product exhibits superior chemical resistance, while maintaining excellent flexibility and gloss retention characteristics.

**CHARACTERISTICS:**

- < Superior chemical resistance
- < Excellent exterior weathering durability
- < Excellent humidity resistance
- < Contains n-methyl pyrrolidone co-solvent

**APPLICATION:** **HD-6000** crosslinked with water-dispersible isocyanates may be spray applied using single-component equipment. The workable potlife is approximately 3 hours at the suggested crosslinker ratio of 2.0 to 1.0 NCO / OH.

**CURING:** **HD-6000**, crosslinked with a water dispersible isocyanate, will dry to a hard film in 30 minutes at ambient room temperature (65 – 70°F) and humidity (RH 50%). Ultimate cured properties will take about 3 -5 days to develop. If heat is available, the ultimate properties can be attained in shorter time. Typical oven drying temperatures and dwell times for aqueous coatings are sufficient to produce optimal film properties.

### PHYSICAL PROPERTIES

<b>SOLIDS</b>	35 (±1%)
<b>VISCOSITY</b>	50-500 cps
<b>DENSITY</b>	8.8 lbs/gal
<b>pH</b>	7.5 - 10.0
<b>VOC CONTENT</b>	126 gm/l (as supplied)
<b>OH EQUIVALENT WT.</b>	3,100 (as supplied)

### TENSILE PROPERTIES

(TESTED AT 20 INCHES/MINUTE)	
<b>ELONGATION</b>	230 %
<b>TENSILE STRENGTH</b>	7000 psi
<b>100% MODULUS</b>	4850 psi
<b>200% MODULUS</b>	6800 psi
<b>300% MODULUS</b>	NA